



**DURACAT  
PRE-CATALYZED  
WATER BASED EPOXY**

**3541 Line**

Type	Sheen	Spread Rate	Recommended Application	Thinner	Clean Up	DRY TIME		
						Tack Free	Re-coat	Cure
100% Acrylic Pre-Catalyzed Water Based Epoxy	Egg-Shell	Up to 400 Sq Ft Per Gallon	Brush, Roller, or Spray	Clean Water	Warm Soapy Water	30 Minutes	4 Hours	7 - 10 Days
<b>PRODUCT NAME: DURACAT PRE-CATALYZED WATER BASED EPOXY</b>	This product provides epoxy toughness in a ready-to-use waterborne formula for walls, ceilings and trim. Low VOC and water cleanup make this product ideal for use in occupied areas. The cured film is scrubbable, resists water and common cleaning chemicals, and stands up to abrasion and marring. Excellent adhesion to many surfaces, including existing paint, drywall, primed masonry and primed metal. This product complies with LEED 2009 Green Building Rating System for interior non-flat paints.							
<b>WHERE TO USE:</b>	Metal Wood Masonry Drywall	<ul style="list-style-type: none"> <li>• Interior institutional/commercial high maintenance areas</li> <li>• Upgrade surfaces painted with conventional coatings with a high-performance protection system with excellent adhesion</li> <li>• Corrosion and Chemical resistant</li> <li>• Hospitals and Schools</li> <li>• Institutional dining and kitchen areas</li> <li>• Suitable for use in USDA inspected facilities</li> </ul>						
<b>Surface Preparation:</b>	<p><b>New Work:</b> The surface to be coated must be clean and free of oil, grease, rust and other contaminants that could interfere with adhesion.</p> <p><b>Priming –</b>            Ferrous Metal – 2090 Bonding Primer*            Aluminum – Self Priming, 50 Block-It**            Galvanized – Self Priming, 50 Block-It            Wood Interior – 50 Block-It Acrylic Primer Sealer            Drywall/Plaster – Latex Primer Sealer 5790 or No. 50            Concrete – Cured; Self Priming, Un-Cured; 5090 Masonry Sealer            Block – 529-11 Block Filler</p> <p><b>Repaint:</b> The surface to be painted must be clean and free of dirt, chalk, mildew, wax, grease, rust or loose flaking paint. *The min. surface preparation for iron &amp; steel is SSPC-SP2, SSPC-SP6 will result in improved performance. **Galvanized and aluminum should be brush blasted or profiled with a maroon 3M pad to ensure proper adhesion.            Glossy surfaces must be dulled by lightly sanding. Remove sanding dust before paint application. Any exposed substrate should be spot primed with the appropriate primer.</p>							
<b>Application:</b>	Stir DuraCat Pre-Catalyzed Water Based Epoxy thoroughly with a circular, listing motion to assure even pigment dispersion. Roller – Use a short nap enameling cover. Brush – Use a polyester or nylon filament brush. Spray – May be sprayed using conventional or airless equipment. Can be thinned with clean water, up to 20% for spraying. For best results, use quality applicator tools. Do not sacrifice good results by using inexpensive tools. Apply only when surface and air temperatures are between 50°F and 90°F.							
<b>NOTE: Formulated without mercury or lead.</b>								

<b>Resin Type:</b>	100% Acrylic Pre-Catalyzed Water Based Epoxy
<b>Solids:</b>	Volume – 39.5%
<b>Weight Per Gallon:</b>	10.89 lbs.
<b>Viscosity:</b>	90 – 100 (Krebs Units)
<b>Flash Point:</b>	200°F or over (TT-P-141, Method 4293)
<b>Specular Gloss:</b>	15 % @ 60°
<b>Light Reflectance:</b>	95% (White or lightest colors)
<b>Limitations:</b>	<ul style="list-style-type: none"> <li>• Do not apply if material, substrate or ambient temperature is below 50 °F (10 °C). The relative humidity should be below 90%.</li> <li>• Not recommended for floors or for use in immersion service.</li> <li>• Interior Use Only</li> </ul>
<b>Recommended Film Thickness:</b>	Wet – 3.0 to 4.0 mils Dry – 1.0 to 1.5 mils
<b>VOC – VOS Statement:</b>	This product contains a maximum of *** grams of VOC/VOS per liter of coating (** lbs. per gallon)
<b>Cautions:</b>	<p><b>CAUTION!</b> Do not take internally. Close container after each use.</p> <p><b>KEEP OUT OF REACH OF CHILDREN.</b></p>

November 21, 2022

