



**Heavy Duty**  
**Latex/Semi-Gloss**  
**2750 Line**  
 SECTION NO. 2 ADS-309

Type	Sheen	Spread Rate	Recommended Application	Thinner	Clean Up	DRY TIME		
						Tack Free	Re-coat	Cure
Latex	Semi-Gloss	Up to 350 Sq Ft Per Gallon	Brush, Roller, Pad or Spray	Clean Water	Warm Soapy Water	60 Minutes	4 Hours	30 Days
<b>Product Name:</b> 2750 Line Heavy Duty Latex / Semi-Gloss		A professional grade Vinyl Acrylic Semi-Gloss Enamel that exhibits good washing characteristics. May be applied on walls and trim in kitchens, hallways, bathrooms, wherever routine maintenance is required.						
<b>WHERE TO USE:</b>		Drywall                      On interior surfaces such as walls and trim. Plaster Wood Metal Masonry						
<b>Surface Preparation:</b>		Surface to be painted must be clean and free of dirt, chalk, wax, grease, rust or loose, flaking paint. Dirt and chalk should be removed by scrubbing with warm soapy water and thoroughly rinsed with clean water. Wax should be removed with a commercial wax stripper or by solvent cleaning. Grease should be cleaned by using Coronado Sur-Prep 1. Rust must be removed by hand sanding or by conscientious power tool cleaning. Remove loose paint by scraping. Feather sand rough edges to insure a smooth finish coat. Glossy surfaces must be dulled by lightly sanding. remove sanding dust before paint application. Any exposed substrate should be spot primed with the appropriate primer. Priming – Drywall – Self priming, but for best results use 4190 Latex Primer Sealer. Plaster – For best results use No. 50 BlockOut, 2000 Sungard. Wood – Alkyd Primer Undercoat, 37-11 Ferrous Metal – Rust inhibiting metal primer such as 35-11, 2090 or 925-147. Galvanized – Acrylic Primer 36-11 or 180-11. Masonry – Masonry Sealer 43-10, 48-11, Block Filler 946-11.						
<b>Application:</b>		Stir product thoroughly with a circular, lifting motion before you begin to paint. Vinyl Acrylic Semi-Gloss Enamel may be applied by brush, roller, pad or spray techniques, at a rate of application not to exceed 350 square feet per gallon. surface texture and porosity will effect actual yield. For best brush application results, use a quality synthetic bristle brush. For roller application, use a 3/8" nap cover for smooth surfaces, a 1/2" or 3/4" nap cover for semi-rough surfaces and a 1" nap cover for rough surfaces. For spray application, Vinyl Acrylic Semi-Gloss Enamel may be thinned with clean water, up to 10% reduction if necessary. Apply when surface temperature is above 50° F.						
<b>NOTE: Formulated without mercury or lead.</b>								

<b>Resin:</b>	Vinyl Acetate / Acrylic Co-Polymer
<b>Solids:</b>	Weight – 39.4% Volume – 26.5%
<b>Weight Per Gallon:</b>	10.1 lbs.
<b>Viscosity:</b>	95 – 100 (Krebs Units)
<b>Specular Gloss:</b>	40% - 50% @ 60 degrees
<b>Recommended Film Thickness:</b>	Wet – 3.5 to 4.5 mils Dry – 1.0 to 1.22 mils
<b>VOC – VOS Statement:</b>	This product contains a maximum of 3.17 lbs or 250 GPL per gallon.
<b>Cautions:</b>	<b>CAUTION!</b> Do not take internally. Close container after each use. <b>KEEP OUT OF REACH OF CHILDREN.</b>