



PRO - TECH
Latex / Flat Finish

4304 LINE

SECTION NO. 1 ADS 342

Type	Sheen	Spread Rate	Recommended Application	Thinner	Clean Up	DRY TIME		
						Tack Free	Re-coat	Cure
Vinyl Acetate / Acrylic	Flat Enamel	Up to 400 Sq Ft Per Gallon	Brush, Roller, Pad or Airless Spray	Clean Water	Warm Soapy Water	30 Minutes	4 Hours	30 Days
PRODUCT NAME: 4304 LINE Pro - Tech Latex / Flat Enamel		Pro-Tech Flat Latex Wall Paint dries to a flat finish which lends itself to excellent touch-up. Product exhibits good opaque qualities, will cover most colors in one coat. This product is designed for maximum stain and scrub resistance.						
WHERE TO USE:		Drywall Plaster Wood Metal Cement Block	May be applied to interior surfaces where a fashionable flat finish is desirable, such as bedrooms, living rooms, dining rooms or hallways.					
Surface Preparation:		<p>New Work: The surface to be coated must be clean and free of dust, grease, wax, rust, oil, and bleeding stains.</p> <p>Priming: Drywall – Self-Priming, but for best results use #4190 Latex Primer Sealer. Plaster – For best results use #50 Block-Out, #2100 Sungard Wood – Alkyd Primer Undercoat #37-11 Ferrous Metal – Rust inhibiting metal primer such as #35-111, #2090 or #925-147. Galvanized - #36-11 or #180-11. Masonry – Masonry Sealer #43-10 or #48-11. To fill porous block use #946-11 Latex Block Filler.</p> <p>Repaint Work: On previously painted surfaces in good repair, no priming is generally necessary. On glossy surfaces, remove the sheen with sandpaper or steel wool. Patch holes or cracks with appropriate filler. Spot prime bare areas with indicated primer. Remove any oil, chalk, dirt, wax or dust, prior to re-coating. Any loose or flaking paint should be removed and the edges feather sanded to produce a smooth, uniform surface.</p>						
Application:		Stir product thoroughly with a circular, lifting motion to disperse into a homogenous liquid. Roller – 3/8" to 1-1/4" nap, depending on surface texture. Brush – Nylon or polyester filament. Airless Spray – Tip size at atomization pressure will vary with type of equipment, viscosity and temperature. An orifice of .017 - .019 will provide the most satisfactory spray pattern. Best results are more likely obtained by using quality application tools. Do not apply directly over chalky surfaces or bleeding stains.						
NOTE: Formulated without mercury or lead.								

Resin Type:	Vinyl Acetate Acrylic
Solids:	Weight – 60.6% Volume – 42.8%
Weight Per Gallon:	11.78 lbs.
Viscosity:	90 – 100 (Krebs Units)
Specular Gloss:	5 – 10% @ 85 Degrees
Recommended Film Thickness:	Wet – 3.5 to 4.5 mils Dry – 1.2 to 1.6 mils
VOC – VOS Statement:	This product contains less than 3.17 lbs. per gallon or 250 G.P.L.
Cautions:	CAUTION! Do not take internally. Close container after each use. KEEP OUT OF REACH OF CHILDREN.